

# SIGRABOND® Sinter

**Material:** Carbon fiber-reinforced carbon (C/C)

**Application:** High-temperature applications especially for sintering processes

## Material data of SIGRABOND® Sinter

Typical properties	Units	Sinter
Density	g/cm <sup>3</sup>	1.45
Flexural strength	MPa	130
Flexural modulus	GPa	60
Tensile strength	MPa	150



**Graphite Materials & Systems | SGL CARBON GmbH**  
Sales Europe/Middle East/Africa | [cfrc-europe@sglcarbon.com](mailto:cfrc-europe@sglcarbon.com)  
Sales Americas | [cfrc-americas@sglcarbon.com](mailto:cfrc-americas@sglcarbon.com)  
Sales Asia/Pacific | [cfrc-asia@sglcarbon.com](mailto:cfrc-asia@sglcarbon.com)  
[www.cfrc-and-felts.com](http://www.cfrc-and-felts.com) | [www.sglcarbon.com](http://www.sglcarbon.com)

### TDS CFRC-T.00

02 2019/1 E Printed in Germany

®registered trademarks of SGL Carbon SE

This information is based on our present state of knowledge and is intended to provide general notes on our products and their uses. It should therefore not be construed as guaranteeing specific properties of the products described or their suitability for a particular application. Any existing industrial property rights must be observed. The quality of our products is guaranteed under our "General Conditions of Sale".