

SIGRASIC® Standard

Material: Carbon fiber-reinforced silicon carbide (CSiC)

Application: High-temperature applications

Material data of SIGRASIC® Standard

Typical properties	Units	Standard
Density	g/cm ³	1.8
Flexural strength	MPa	140
Flexural modulus	GPa	60
Tensile strength	MPa	350
Interlaminar shear strength	MPa	13
Max. application temperature	°C [°F]	1200 [2200] in vacuum or inert gas
Max. application temperature	°C [°F]	450 [840] in oxygen
Open porosity	%	2



Graphite Materials & Systems | SGL CARBON GmbH
 Sales Europe/Middle East/Africa | cfrc-europe@sglcarbon.com
 Sales Americas | cfrc-americas@sglcarbon.com
 Sales Asia/Pacific | cfrc-asia@sglcarbon.com
www.cfrc-and-felts.com | www.sglcarbon.com

TDS CSiC-S.00

09 2018/1.0 E Printed in Germany

®registered trademarks of SGL Carbon SE

This information is based on our present state of knowledge and is intended to provide general notes on our products and their uses. It should therefore not be construed as guaranteeing specific properties of the products described or their suitability for a particular application. Any existing industrial property rights must be observed. The quality of our products is guaranteed under our "General Conditions of Sale".